

**Amendments to the Claims:**

This listing of claims will replace all prior versions, and listings, of claims in the application:

1. (Original) A single diamond prepared by CVD and having at least one of the following characteristics:

- (i) in the off state, a resistivity  $R_1$  greater than  $1 \times 10^{12} \Omega \text{ cm}$  at an applied field of  $50 \text{ V}/\mu\text{m}$  measured at 300 K;
- (ii) A high breakdown voltage in the off state, and high current with long carrier life time in the on state;
- (iii) an electron mobility ( $\mu_e$ ) measured at 300K greater than  $2400 \text{ cm}^2\text{V}^{-1}\text{s}^{-1}$ ;
- (iv) a hole mobility ( $\mu_h$ ) measured at 300K greater than  $2100 \text{ cm}^2\text{V}^{-1}\text{s}^{-1}$ ; and
- (v) a high collection distance greater than  $150 \mu\text{m}$  measured at an applied field of  $1 \text{ V}/\mu\text{m}$  and 300 K.

2. (Original) A single crystal diamond according to claim 1 which has resistivity greater than  $2 \times 10^{13} \Omega \text{ cm}$  at an applied field of  $50 \text{ V}/\mu\text{m}$  measured at 300 K.

3. (Original) A single crystal diamond according to claim 1 which has a resistivity  $R_1$  greater than  $5 \times 10^{14} \Omega \text{ cm}$  at an applied field of  $50 \text{ V}/\mu\text{m}$  measured at 300 K.

Attorney Docket No. 248810US-2 CONT  
Inventor: Geoffrey A. SCARSBROOK et al  
Preliminary Amendment filed: February 13, 2004

4. (Currently Amended) A single crystal diamond according to ~~any one of the preceding claims~~ claim 1 which has a  $\mu\tau$  product measured at 300 K greater than  $1.5 \times 10^{-6} \text{ cm}^2 \text{ V}^{-1}$  where  $\mu$  is the mobility and  $\tau$  is the lifetime of the charge carriers.

5. (Original) A single crystal diamond according to claim 4 which has a  $\mu\tau$  product measured at 300 K of greater than  $4.0 \times 10^{-6} \text{ cm}^2 \text{ V}^{-1}$ .

6. (Original) A single diamond according to claim 4 which has a  $\mu\tau$  product measured at 300 K greater than  $6.0 \times 10^{-6} \text{ cm}^2 \text{ V}^{-1}$ .

7. (Currently Amended) A single crystal diamond according to ~~any one of the preceding claims~~ claim 1 which has an electron mobility ( $\mu_e$ ) measured at 300 K greater than  $3000 \text{ cm}^2 \text{ V}^{-1} \text{ s}^{-1}$ .

8. (Original) A single crystal diamond according to claim 7 which has an electron mobility ( $\mu_e$ ) measured at 300 K greater than  $4000 \text{ cm}^2 \text{ V}^{-1} \text{ s}^{-1}$ .

9. (Currently Amended) A single crystal diamond according to ~~any one of the preceding claims~~ claim 1 which has a hole mobility measured at 300 K greater than  $2500 \text{ cm}^2 \text{ V}^{-1} \text{ s}^{-1}$ .

Attorney Docket No. 248810US-2 CONT  
Inventor: Geoffrey A. SCARSBROOK et al  
Preliminary Amendment filed: February 13, 2004

10. (Original) A single crystal diamond according to claim 9 which has a hole mobility measured at 300 K greater than  $3000 \text{ cm}^2 \text{V}^{-1} \text{s}^{-1}$ .

11. (Amended) A single crystal diamond according to ~~any one of the preceding claims~~ claim 1 which has a collection distance measured at 300 K greater than  $400 \mu\text{m}$ .

12. (Original) A single crystal diamond according to claim 11 which has a collection distance measured at 300 K greater than  $600 \mu\text{m}$ .

13. (Currently Amended) A single crystal diamond according to ~~any one of the preceding claims~~ claim 1 which has each of the characteristics (i), (ii), (iii), (iv) and (v).

14. (Currently Amended) A method of producing a single crystal diamond according to ~~any one of the preceding claims~~ claim 1 which includes the steps of providing a diamond substrate having a surface which is substantially free of crystal defects, providing a source gas, dissociating the source gas and allowing homoepitaxial diamond growth on the surface which is substantially free of crystal defects in an atmosphere which contains less than 300 parts per billion nitrogen.

Attorney Docket No. 248810US-2 CONT  
Inventor: Geoffrey A. SCARSBROOK et al  
Preliminary Amendment filed: February 13, 2004

15. (Original) A method according to claim 14 wherein the substrate is a low birefringence type 1a or 11b natural, 1b or 11a high pressure/high temperature synthetic diamond.

16. (Original) A method according to claim 14 wherein the substrate is a CVD synthesized single crystal diamond.

17. (Currently Amended) A method according to ~~any one of claims 14 to 16~~ claim 14 wherein the surface on which diamond growth occurs has a density of surface etch features related to defects below  $5 \times 10^3/\text{mm}^2$ .

18. (Currently Amended) A method according to ~~any one of claims 14 to 16~~ claim 14 wherein the surface on which diamond growth occurs has a density of surface etch features related to defects below  $10^2/\text{mm}^2$ .

19. (Currently Amended) A method according to ~~any one of claims 14 to 18~~ claim 14 wherein the surface on which the diamond growth occurs is subjected to a plasma etch to minimise surface damage of the surface prior to diamond growth.

Attorney Docket No. 248810US-2 CONT  
Inventor: Geoffrey A. SCARSBROOK et al  
Preliminary Amendment filed: February 13, 2004

20. (Original) A method according to claim 19 wherein the plasma etch is an *in situ* etch.

21. (Currently Amended) A method according to claim 19 ~~or claim 20~~ wherein the plasma etch is an oxygen etch using an etching gas containing hydrogen and oxygen.

22. (Original) A method according to claim 21 wherein the oxygen etch conditions are a pressure of 50 to 450 x 10<sup>2</sup>Pa, an etching gas containing an oxygen content of 1 to 4%, an argon content of up to 30% and the balance hydrogen, all percentages being by volume, a substrate temperature of 600 to 1100°C, and an etch duration of 3 to 60 minutes.

23. (Currently Amended) A method according to claim 19 ~~or claim 20~~ wherein the plasma etch is a hydrogen etch.

24. (Original) A method according to claim 23 wherein the hydrogen etch conditions are a pressure of 50 to 450 x 10<sup>2</sup>Pa, an etching gas containing hydrogen and up to 30% by volume argon, a substrate temperature of 600 to 1100°C and an etch duration of 3 to 60 minutes.

Attorney Docket No. 248810US-2 CONT  
Inventor: Geoffrey A. SCARSBROOK et al  
Preliminary Amendment filed: February 13, 2004

25. (Currently Amended) A method according to ~~any one of claims 19 to 24~~ claim 19 wherein the surface on which the diamond growth occurs is subjected to both an oxygen and a hydrogen etch to minimise surface damage of the surface prior to diamond growth.

26. (Original) A method according to claim 25 wherein the oxygen etch is followed by a hydrogen etch.

27. (Currently Amended) A method according to ~~any one of claims 19 to 26~~ claim 19 wherein the surface  $R_A$  of the surface on which the diamond growth occurs is less than 10 nanometers prior to that surface being subjected to the plasma etching.

28. (Currently Amended) A method according to ~~any one of claims 14 to 27~~ claim 14 wherein the diamond growth takes place in an atmosphere which contains less than 100 ppb nitrogen.

29. (Currently Amended) A method according to ~~any one of claims 14 to 28~~ claim 14 wherein the surface on which diamond growth occurs is substantially a {100}, {110}, {113} or {111} surface.

Attorney Docket No. 248810US-2 CONT  
Inventor: Geoffrey A. SCARSBROOK et al  
Preliminary Amendment filed: February 13, 2004

30. (Currently Amended) A method according to ~~any one of claims 14 to 29~~ claim 14 wherein the dissociation of the source gas occurs using microwave energy.

31. (Amended) The use of a single crystal diamond according to ~~any one of claims 1 to 13~~ claim 1 in an electronic application.

32. (Currently Amended) The use of a single crystal diamond according to ~~any one of claims 1 to 13~~ claim 1 as a detector element or switching element.

33. (Currently Amended) The use of a single crystal diamond of ~~any one of claims 1 to 13~~ claim 1 as a component in an opto-electric switch.

34. (Currently Amended) A detector element or switching element comprising a single crystal diamond according to ~~any one of claims 1 to 13~~ claim 1.